




TPM

BoPP matt film, treated



PROPERTIES

- Both sides matt silk appearance
- Non-treated surface can be easily corona treated, if required
- High dimensional stability

TYPICAL APPLICATIONS

- Matt adhesive tapes, which can be easily printed (after a proper corona treatment) on the non-treated side
- General wrapping

ROLL SIZE AVAILABILITY*

Film	Standard Length (m)	4x ** (m)	7x (m)
TPM 30	2,100	8,400	14,700
TPM 35	1,800	7,200	12,600
Outside diameter - core 76 mm	305 mm	588 mm	
Outside diameter - core 152 mm	337 mm	605 mm	783 mm

*Regional availability of roll sizes (multiples of standard length)-please refer to the corresponding Sales Representative

**Length rolls on 152 mm cores will be produced with reduced length in Europe to maintain roll diameters below 600 mm

Properties	Method	Unit	Ref.	Typical values	
Nominal thickness	Internal method	µm		30	35
Unit weight		g/m ²		27.0	31.5
Yield		m ² /kg		37.0	31.7
Tensile strength	ASTM D882	N/mm ²	MD TD	140 270	
Elongation at break		%	MD TD	170 50	
Gloss (45°)	ASTM D2457	Gloss Unit		12	
Thermal shrinkage	OPMA TC4(a)	%	MD TD	6.0 2.0	
Treatment level	ASTM D2578	mN/m		40	

Tolerance		
Weight	≤ 1.000 kg	± 20%
	1.001-10.000 kg	± 10%
	> 10.000 kg	± 5%

STORAGE, HANDLING AND APPLICATION

TPM does not require special storage conditions. A storage temperature below 30°C is recommended in order to minimise the deterioration of the film properties in general. It is advisable to turn over the inventory according to the delivery date (first in-first out). The film should be conditioned in the operating environment at least for 24 hours before processing. TPM is suitable for use up to 6 months from the date of production.

INDICATION OF SURFACE TREATMENT

TPM is usually supplied with treatment on the inside surface (TI).
TPM can be supplied with treatment on the outside surface (TO). This must be agreed with our sales representative before processing the order.

FOOD CONTACT

TPM complies with EC and FDA regulations. Specific documents and MSDS are available on request.

The property values represented in the table do not constitute product specifications, but represent the average or typical values. Use of this information is limited to the specific recipient. While the information is accurate to the best of our knowledge as of the date compiled, it is limited to the information as specified. No representation or warranty, expressed or implied, is made regarding the information, or its completeness or fitness to a particular use. The user is solely responsible for all determinations regarding use and we disclaim liability for any loss or damage that may occur from the use of this information. Ti does not guarantee the typical (or other) values.