




# LGL

**BoPP white voided film, wrap around label, both sides high gloss, very high yield, treated**



## PROPERTIES

- Very high yield
- White pearlescent high gloss appearance on both sides
- Consistent slip

## TYPICAL APPLICATIONS

- Wrap around label (WAL); reel fed technology
- Rotogravure, flexographic, off-set or UV printing
- High print definition, premium print

## ROLL SIZE AVAILABILITY\*

Film	Standard Length (m)	4x ** (m)	7x (m)
LGL 33	1,900	7,600	13,300
LGL 38	1,650	6,600	11,550
LGL 47	1,300	5,200	9,100
Outside diameter - core 76 mm	305 mm	588 mm	
Outside diameter - core 152 mm	337 mm	605 mm	783 mm

\*Regional availability of roll sizes (multiples of standard length)-please refer to the corresponding Sales Representative

\*\*Length rolls on 152 mm cores will be produced with reduced length in Europe to maintain roll diameters below 600 mm

Properties	Method	Unit	Ref.	Typical values		
Nominal thickness	Internal method	µm		33	38	47
Unit weight		g/m <sup>2</sup>		20.5	23.6	29.1
Yield		m <sup>2</sup> /kg		48.9	42.4	34.3
Tensile strength	ASTM D882	N/mm <sup>2</sup>	MD TD	90 150		
Elongation at break		%	MD TD	115 30		
Light transmission	ASTM D1003	%		28	25	23
Gloss (45°)	ASTM D2457	Gloss Unit		90		
Dynamic cof	ASTM D1894		NT/NT	0.25		
Thermal shrinkage	OPMA TC4(a)	%	MD TD	5.0 2.0		
Treatment level	ASTM D2578	mN/m		38		

Tolerance		
Weight	≤ 1.000 kg	± 20%
	1.001-10.000 kg	± 10%
	> 10.000 kg	± 5%

## STORAGE, HANDLING AND APPLICATION

LGL does not require special storage conditions. A storage temperature below 30°C is recommended in order to minimise the deterioration of the film properties in general. It is advisable to turn over the inventory according to the delivery date (first in-first out). The film should be conditioned in the operating environment at least for 24 hours before processing. LGL is suitable for use up to 6 months from the date of production.

## INDICATION OF SURFACE TREATMENT

LGL is usually supplied with treatment on the outside surface (TO). LGL can be supplied either with treatment on the inside surface (TI) or treated on both sides (DO, DI). This must be agreed with our sales representative before processing the order.

## FOOD CONTACT

LGL complies with EC and FDA regulations. Specific documents and MSDS are available on request.

The property values represented in the table do not constitute product specifications, but represent the average or typical values. Use of this information is limited to the specific recipient. While the information is accurate to the best of our knowledge as of the date compiled, it is limited to the information as specified. No representation or warranty, expressed or implied, is made regarding the information, or its completeness or fitness to a particular use. The user is solely responsible for all determinations regarding use and we disclaim liability for any loss or damage that may occur from the use of this information. Ti does not guarantee the typical (or other) values.